



# CAMATHICK PTR CONS



## Synthetic Thickener for Reactive Printing

### SALIENT FEATURES

- ▶ Generates high viscosity
- ▶ Easy to disperse & fast viscosity build – up
- ▶ Does not require very high-speed stirring
- ▶ Gives smooth swelling & homogeneous blend
- ▶ Have Pseudoplastic property to give excellent print definition
- ▶ No clogging of screens even in finer mesh & high speed
- ▶ Excellent brightness, levelness
- ▶ Better quality Prints than conventional thickeners
- ▶ Higher colour yield observed with majority of dyestuffs
- ▶ Excellent stability of stock thickening paste with all chemicals added
- ▶ No cooking / heating required. Only mild stirring is sufficient
- ▶ Environmentally friendly product
- ▶ APEO / NPEO, Formaldehyde free

### CHARACTERISTICS

Appearance	: Off – white pourable viscous liquid
Chemical Nature	: Polymeric compound
Dispersibility	: Excellent with water in all proportions
pH	: 7.5 ± 0.2
Compatibility	: Excellent with all reactive printing ingredients

### APPLICATION

Substrate	: Cellulosic fabric
Machines	: Printing equipments & machines
Function	: Thickener in Reactive Printing
Guide Recipes	: <b>(1) Preparation of Stock Paste</b> – (for fixation by ageing)

<b>CAMATHICK PTR CONS</b>	<b>4.0 – 4.5 parts</b>
Sodium bicarbonate	3.0 – 3.5 parts
Resist Salt	1.0 – 2.0 parts
Urea	5.0 – 8.0 parts

-----  
Bulk with water to 100 parts  
-----

#### *Preparation of Print Paste –*

<b>Camex Dyestuff</b>	X parts
Water (To paste the dye)	5 – 10 parts
<b>Stock Paste</b>	85 – 90 parts

-----  
Bulk 100 parts  
-----

Print – dry – steam at 102°C for 8-10 minutes – wash off



# CAMATHICK PTR CONS



## Synthetic Thickener for Reactive Printing

### (2) Preparation of Stock Paste – (for fixation by silicate)

<b>CAMATHICK PTR CONS</b>	<b>4.0 – 4.5 parts</b>
Resist Salt	1.0 – 2.0 parts
Urea	5.0 – 8.0 parts
-----	
Bulk with water to	100 parts
-----	

### Preparation of Print Paste –

<b>Camex Dye stuff</b>	<b>X parts</b>
Water (To paste the dye)	5 – 10 parts
<b>Stock Paste</b>	<b>85 – 90 parts</b>
-----	
Bulk	100 parts
-----	

Print – dry – Silicate pad – dwell for minimum of 12 hours – wash off

### SPECIAL REMARKS

<b>Storage Stability</b>	: Minimum 6 months under standard conditions of storage. Avoid heat, sunlight & moisture
<b>Container</b>	: 50 kg HDPE barrels

Disclaimer: All recommendations for the use of our products, whether given by us in writing, orally or to be implied from the results of trials, are based on our present state of knowledge & experience. Owing to the variation in local application conditions, they can not be claimed to be complete. Hence, we can not accept any responsibility thereof. All claims, liabilities – also with a view to claim of third parties – are excluded. It is advised to conduct lab & bulk trials before using in bulk production.